

DENKA BEFORM

Cementitious Quick Hardening Additive

Description

DENKA BEFORM is a quick-hardening cement admixture developed using DENKA's long-established cutting-edge technology in cementitious products.

Features

- Handling time can be adjusted to between 20 minutes and 2 hours by using general setting modifiers such as tartaric acid or dedicated setting modifier DENKA SETTER D-300
- Excellent initial strength (10-30MPa can be obtained in 6 hours)
- Excellent crack resistance
- Reduced self-shrinkage and drying shrinkage due to expansion characteristics

Applications

- Quick-hardening grout
- Self-leveling material
- Quick-hardening repairing material
- Decorative mortar
- Instant demoulding of small products

Packaging and General Information

- Packaging: 20kg bags
- Appearance: Greyish-white powder
- Specific weight: 2.92
- Blaine specific surface area: 6000cm²/g
- Additive amount: 15~20% by cement weight

Physical Properties of Mortar

General properties (typical values)

- Quick hardening additive (QHA): DENKA BEFORM, other CAC (Calcium aluminate cement)
- Retarding agent: DENKA SETTER D-300 for BEFORM, Tartaric acid for CAC
- Sand: ISO sand
- Water: tap water
- Base mix proportion; Binder/Sand = 1.0/1.5, Water/Binder = 0.30
- Length change; uniaxial confined method, cured in the water at 20°C after 1 day

OPC	Binder		Retarding agent (QHAx%)	Flow with 25 drops (mm)	Handling time(min)	Compressive strength (MPa)		
	Product	Ratio				3 hours	6 hours	1 day
100	—	—	—	153	300	—	—	32.0
90	BEFORM	10	0.26 ¹	209	55	7.1	15.4	35.9
85		15	0.26 ¹	212	56	11.4	24.4	45.4
75		25	0.28 ¹	215	68	16.3	37.5	73.2
80	CAC	20	0.11 ²	187	29	6.8	8.3	11.8
20		80	0.27 ²	162	30	5.1	18.4	55.2
10		90	0.13 ²	168	30	19.6	43.5	59.5

¹DENKA SETTER D-300

²Tartaric acid

Handling Precautions

- Refer to the Safety Data Sheet (SDS) before use.
- Wear protective gear (goggles, mask, gloves, and rubber boots) while handling the product. Do not dispose of the product in drains.
- Once opened, the product should be used up completely. Otherwise, reseal for storage.
- The product should be stored in a dry area, indoors, and out of direct sunlight.
- For further information, please contact DENKA.

Limitation of Liability

- The information contained in this brochure provides general advice for potential customers of DENKA about the basic properties and characteristics of various DENKA products (hereafter referred to as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in this brochure.
- Nothing in this brochure will be deemed to create any express or implied warranty or obligation of DENKA with respect to the Product Information or its use, including, but not limited to, any warranty of merchantability, fitness for a particular purpose, or infringement of any intellectual property rights.
- Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA, including descriptions of the conditions of use, warnings, and other cautionary instructions.
- DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.

Denka
<http://www.denka.co.jp/eng>

Denka Co. Ltd.

Special Cement Additives Department
TEL: +81-3-3507-5465 FAX: +81-3-3507-5085

-China-

**DENKA INFRASTRUCTURE
TECHNOLOGIES SHANGHAI**
ROOM 2807, NEW HONGQIAO
CENTER BLDG
NO.83 LOUSHANGUAN RD,
CHANG NING AREA, SHANGHAI CHINA
TEL: +86-21-6236-5510
FAX: +86-21-6236-5505

-Asia-

**DENKA INFRASTRUCTURE
TECHNOLOGIES PTE LTD**
8 Jurong Town Hall Road #07-01
JTC Summit, SINGAPORE 609434
TEL:+65-6216-0580
FAX:+65-6224-3840
**DENKA CONSTRUCTION
SOLUTIONS MALAYSIA SDN BHD**
No.18, Jalan Utas 15/7, Seksyen 15,
40200 Shah Alam, Selangor Darul Ehsan,
Malaysia
TEL:+603-5510-8810
FAX:+603-5518-8202

-Europe-

DENKA CHEMICALS GMBH
WEHRHAHN-CENTER, CANTADOR STR.3,
DUSSELDORF, GERMANY
TEL: +49-211-130990
FAX: +49-211-329942